

CAPA FLEX

Gel Adhesive C2TE

Description

CAPA FLEX is a gel-like texture adhesive, which provides the maximum performance of workability and security in the tiling. Classified according to UNE EN12004 standard and ISO 13007 as C2TE. Its composition, based on modified resins, gives it an excellent workability. It also has rheological agents, which guarantee a very high thixotropy and an extended open time that gives a total grip.

Advantage

- Gel adhesive
- High thixotropy
- Extended open time

Technical Data

Appearance	White and Grey powder
Grain size	< 0.6 mm
Powder density	1.5 kg/l
Paste density	1.7 kg/l
Mixing water	5.4-5.6 l/bag
Pot life	3 hours
Open time	20 minutes
Adjustment time	20 minutes
Slip	≤ 0.5 mm
Adhesive strength under normal conditions	≥ 2 N/mm ²
Adhesive strength after water cycle	≥ 1 N/mm ²
Adhesive strength after heat cycle	≥ 1 N/mm ²
Adhesive strength after freeze/thaw cycling	≥ 1 N/mm ²
Coverage	1.2-1.3 kg/m ² /mm thickness
Coming into service at +23°C	Light traffic 1 day Heavy traffic 2 days
Maximum thickness	15 mm

Application Surfaces

Conventional surfaces and cement based mortar floors and finishes. Concrete, laminated plaster and plasterboard. Cellular Concrete. The application surface must be hard, perfectly set and free from dust, paint, oil, etc.

Application Information

For Internal & External use to fix all types of ceramic tiles, vitrified tiles, glass mosaics & natural stones. Can be used for Domestic & Commercial applications. A double glue technique should be used for tiles larger than 900 cm² (30 cm x 30 cm)

Application Instruction

1. Add water and mix by hand or mechanically until you obtain a smooth paste of a workable consistency (7,51-8,51)
2. Leave the paste to stand for 5 minutes and mix again before applying.
3. Spread the paste on the surface in sections of a surface area no larger than 2 m², combining with suitable trowel. If double gluing is required, spread the mixture over the back of the tile as well.
4. Put the ceramic tiles on top of the freshly-laid adhesive, pressing lightly to ensure that the whole tile surface comes into contact with the adhesive, filling any grooves.
5. Leave a joint of a width of at least 2 mm between indoor tiles and at least 5 mm between outdoor tiles. Wait 24 hours before grouting wall tiles and 48 hours before grouting floor tiles.
6. Respect all perimeter and structural joints. Place one partition joint every 50 m² for indoor floor tiling, and one every 30 m² for outdoor floor tiling.

Available Pack Size

CAPA FLEX is available in 25 kg sacks with moisture-proof plastic lining, dispatched on shrink-wrapped pallets weighing a total of 1,600 kg (64 bags).

Warnings And Recommendations

- Do not apply this product when frost or rain are forecasted.
- For plaster surfaces, use Capagel Flex. Avoid applying on dead plaster or weak renderings.
- In extreme weather conditions (wind or high temperatures), the product will dry more quickly than usual. This will result in a shorter open time.
- In high temperatures, windy conditions or if the application surface is very absorbent, it is advisable to moisten the surface and wait for the film of water to disappear before applying the product.
- Check periodically, that a surface film has not formed on the adhesive paste once it has been spread onto the surface. If a film has formed, remove the product and apply a fresh coat.
- Check that the paste is sticky enough by periodically lifting one of the tiles already in place to ensure that it is well stuck down.
- Use within 1 year of date of packaging. Store the product in its original packaging in a dry, covered place protected from humidity.

Warranty

Topkrete Sdn Bhd warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to TOPKRETE SDN BHD shall be limited to replacement of the material proven to be defective, and TOPKRETE SDN BHD shall in no case be liable otherwise or for incidental or consequential damages. **TOPKRETE SDN BHD MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED.** User shall determine the suitability of the product for its intended use and assume all risks and liability in connection therewith.

Important note

The recommendations for use are based on our own knowledge and experience. The technical data provided have been obtained under normal laboratory conditions, and may therefore vary according to the environmental conditions in the place where the product is used. As the application conditions are beyond our control, the information provided here does not imply that the company accepts responsibility for any variations.

Malaysia Office: Topkrete Sdn Bhd (597943-M)
19-G, Blok A, Jalan Atmosphere 3,
Pusat Perniagaan Atmosphere,
Bandar Putra Permai,
43300 Seri Kembangan,
Selangor Darul Ehsan, Malaysia
Tel: +603- 8957 8999 Fax: +603-8959 1661
Email: info@topkrete.com
www.topkrete.com

Spain Office: Cementos CAPA, S.L
Muelle de Ribera-Poniente, s/n.
Puerto de Almeria, 04002 Almeria
(Espana/Spain/Espagne/Espanha)
T: + (34) 950 620 620
www.capa.es

Technology from



Spain