

DECKRETE RP

Heavy Duty Car Park Flooring (3 mm)

Description

Deckrete RP is a solvent free polyurethane car park deck coating system to provide hard wearing and crack resistant for internal and external car park area floor such as loading bay and ramp.

Uses

Deckrete RP is used for internal and external car park ramp and loading bay where a decorative appearance, durable, and anti-slip properties are required.

Advantage


- Aesthetically attractive
- Reduces tyre noise
- Hard wearing
- Fire resistant
- Anti-slip
- Solvent free
- Fast Installation
- Excellent bond strength
- Resistant to cracking
- UV resistant

Standard Colour



Physical Properties	
Adhesive Strength (ASTM C 321)	>1.5 N/mm ²
Shore D Hardness (ASTM D 2240)	70
Elongation at Break (ASTM D412)	70%
Abrasion Resistant (ASTM D 1044) Taber CS-10	40 mg/1000 cycles/1kg
TRRL Slip Resistance (BS 7976)	80 Dry 45 Wet

System Design



- Deckrete UV
- Deckrete SC
- Aluminium Oxide
- Deckrete CP Primer
- Substrate

Appearance

Deckrete RP provides a anti-slip finish with a glossy surface.

Design Life

10 years, subject to proper maintenance.

Specification Detail	Coverage
Deckrete UV	0.12 kg/m ²
Deckrete SC	0.7 kg/m ²
Aluminium Oxide	3.5 kg/m ²
Deckrete FC	0.7 kg/m ²
Deckrete CP Primer	0.3 kg/m ²

Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm², free from dust, loose particles and contaminants such as oils, fats, greases, paint residues, chemicals, algae and laitance. Substrate moisture levels should be no greater than 75% RH. BS 8204 SR 2 – 5 mm at every 3 meter.

Application

Please read Deckrete RP Method Statement for requirements of surface preparation, mixing and application.

Cure Schedule	35°C
Light Traffic	12 hours
Full Traffic	24 hours
Full Chemicals Cure	5 days

Maintenance

Regular cleaning of Deckrete RP may be carried out using a rotary scrubbing machine with a water miscible cleaning agent.

Temperature Resistance

Deckrete RP is resistant to temperature cycles up to 70°C. Extended periods at these temperature and above will make material susceptible to chemical attack and abrasion wear.

Chemical Resistance

Examination for this was made with six common chemicals:-

- ✓ engine oil (used)
- ✓ brake fluid
- ✓ anti-freeze mixture
- ✓ saturated salt water
- ✓ battery acid
- ✓ petrol

Technical Support

Topkrete provide a technical advisory service supported by a team of specialist in the field.

Health & Safety

For further information, refer to the product Material Safety Data Sheet, available upon request.

Additional Information

Topkrete manufacturers and offers a wide range of complementary products which includes waterstop, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spelled concrete are available.

Warranty

Topkrete Sdn Bhd warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to TOPKRETE SDN BHD shall be limited to replacement of the material proven to be defective, and TOPKRETE SDN BHD shall in no case be liable otherwise or for incidental or consequential damages. **TOPKRETE SDN BHD MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED.** User shall determine the suitability of the product for its intended use and assume all risks and liability in connection therewith.

Important note

Topkrete products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which may be obtained on request. Whilst Topkrete endeavors to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it shall not, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it.

Topkrete Sdn Bhd (597943-M)

Office : 19-G, Blok A, Jalan Atmosphere 3,
Pusat Perniagaan Atmosphere,
Bandar Putra Permai,
43300 Seri Kembangan,
Selangor Darul Ehsan. Malaysia
Tel: +603- 8957 8999 Fax: +603-8959 1661
Email: info@topkrete.com
www.topkrete.com

Factory : No.3, Jalan Utama 1/12,
Taman Perindustrian Puchong Utama,
47100 Puchong,
Selangor Darul Ehsan. Malaysia.
Tel : +603-80631883 Fax: +603-80631983