

Deckrete SL 200

Self Smoothing Epoxy Flooring (2 mm)

Description

Deckrete SL 200 is a self leveling, medium to heavy duty epoxy flooring system to provide an easy to clean, dust free floor with excellent mechanical and chemical resistance.

Uses

Deckrete SL 200 is widely used on industrial and commercial floors in laboratories, schools, plant rooms, factories, engineering workshops, hospital clean rooms and many more applications, where appearance and ease of cleaning are paramount.

Advantage

- Self-leveling
- Seamless
- Hard wearing
- Abrasion resistant
- Solvent free
- Easy to clean
- Fast Installation
- Chemical resistant

Standard Colour



SIGNAL YELLOW OXIDE RED OXIDE GREEN LEAF GREEN PASTEL BLUE



LIGHT GREY MID GREY DARK GREY ORANGE BLACK

Appearance

Deckrete SL 200 provides a smooth finish with a glossy surface.

Design Life


6 – 8 years, subject to proper maintenance.



Physical Properties

Compressive Strength (ASTM C 109)	60 N/mm ²
Flexural Strength (ASTM D 790)	40 N/mm ²
Tensile Strength (ASTM D 648)	25 N/mm ²
Adhesive Strength (ASTM C 321)	>2.5 N/mm ²
Shore D Hardness (ASTM D 2240)	80
Abrasion Resistant (ASTM D 1044) Taber CS-10	80 mg/1000 cycles/1kg

System Design



Specification Detail	Coverage
Deckrete EP	0.2 kg/m ²
Deckrete SL 200 (2mm)	3.6 kg/m ²

Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm², free from dust, loose particles and contaminants such as oils, fats, greases, paint residues, chemicals, algae and laitance. Substrate moisture levels should be no greater than 75% RH. BS 8204 SR 2 – 5 mm at every 3 meter.

Application

Please read Deckrete SL 200 Method Statement for requirements of surface preparation, mixing and application.

Cure Schedule	35°C
Light Traffic	12 hours
Full Traffic	24 hours
Full Chemicals Cure	5 days

Maintenance

Regular cleaning of Deckrete SL 200 may be carried out using a rotary scrubbing machine with a water miscible cleaning agent.

Temperature Resistance

Deckrete SL 200 is resistant to temperature cycles up to 60°C. Extended periods at these temperature and above will make material susceptible to chemical attack and abrasion wear.

Chemical Resistance

Please refer to the (Chemical Resistance Chart) for actual resistance to specific chemicals / reagents.

Technical Support

TOPKRETE offers a comprehensive range of high performance, quality products. TOPKRETE offers a technical support package to specifiers and contractors which include assistance with product selection and technical advice from staff with unrivalled experience in the industry.

Health & Safety

For further information, refer to the product Material Safety Data Sheet, available upon request.

Additional Information

Topkrete manufacturers and offers a wide range of complementary products which includes waterstop, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spelled concrete are available.

Warranty

Topkrete Sdn Bhd warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to TOPKRETE SDN BHD shall be limited to replacement of the material proven to be defective, and TOPKRETE SDN BHD shall in no case be liable otherwise or for incidental or consequential damages. **TOPKRETE SDN BHD MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED.** User shall determine the suitability of the product for its intended use and assume all risks and liability in connection therewith.

Important note

Topkrete products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which may be obtained on request. Whilst Topkrete endeavors to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it shall not, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it.

Topkrete Sdn Bhd (597943-M)

Office : 19-G, Blok A, Jalan Atmosphere 3,
Pusat Perniagaan Atmosphere,
Bandar Putra Permai,
43300 Seri Kembangan,
Selangor Darul Ehsan, Malaysia
Tel: +603- 8957 8999 Fax: +603-8959 1661
Email: info@topkrete.com
www.topkrete.com

Factory : No.3, Jalan Utama 1/12,
Taman Perindustrian Puchong Utama,
47100 Puchong,
Selangor Darul Ehsan, Malaysia.
Tel : +603-8063 1883 Fax: +603-8063 1983